

**LDPE - ARGETENA I<sup>®</sup> 035**

<b>CHARACTERISTIC</b>	<b>UNITS</b>	<b>VALUE</b>	<b>TEST METHOD</b>
Appearance	Uniform colour granules, without mechanical impurities.		Visual
Density at 23°C	g/cm <sup>3</sup>	0.919÷0.923	ISO 1183-87 Method D  ASTM D 1505-85 (90)
Melt flow index (190°C, 2.16 kg)	g/10'	2 ± 0.4	ASTM D 1238-94a Method A  ISO 1133-91 Method A
Tensile strength at break, min.	MN/m <sup>2</sup>	13	ASTM D 638 M-93
Elongation at break, min.	%	500	ASTM D 638 M-93
Tensile strength at yield limit, min.	MN/m <sup>2</sup>	8.5	ASTM D 638 M-93
Gloss (45°), (on film of 0.04±0.005 mm, obtained by extrusion at max. 165±2°C), min.	—	60	ASTM D 2457 – 90